



Technical Product Data Sheet

Market Scandinavia

WAB Wet Area Board	Special board, hydrophobic
Thickness x width x length (mm)	12,5 x 900 x 2400 12,5 x 900 x 2700 12,5 x 1200 x 2700 other dimensions on request
Edge	TE / tapered edge
Tolerance (width)	+ 0 mm / - 3 mm
Weight	10.8 kg/m ²
Reaction to fire	A2-s1, d0
Classification acc. to EN 15283-1	GMH1I
Total water absorption after 2 hours immersion	< 2 %
Surface water absorption 2 h Cobb test	< 100 g/m ²
Moisture expansion 50 % RH to 90 % RH	0,3 mm /m
Thermal expansion coefficient at 50 – 60 % RH	0,013 mm/mK
Mould resistance	no mould - after 12 months 30 °C 95 % RH - after 4 weeks with mould seeds
Bending radius	≥ 3 m
Flexural strength, MD E-modulus Breaking load	4000 N/mm ² > 610 N
Flexural strength, CD E-modulus Breaking load	3500 N/mm ² > 280 N
Water vapour resistance factor	9
Surface hardness (acc. to EN 15283-1)	Type I
WAB compound (LaHydrofix)	Compound, ready for use
Consumption	0,5 kg/m ²
Content per bucket	25 kg

Status: 05 September 2008

Lafarge Gips GmbH, Frankfurter Landstraße 2-4, D-61440 Oberursel, Germany
Phone: +49 (0) 61 71 - 61 - 33 33, www.lafarge-gips.de

